

Teknisk datablad - 30012 Natronfeldspat

Kemisk formel: $\text{Na}_2\text{O} \cdot \text{Al}_2\text{O}_3 \cdot 6\text{SiO}_2$ Molvægt: 524,29

Kemisk analyse

	Tolerance		
	Benchmark	Fra:	Til:
	(%)	(%)	(%)
SiO ₂	70,20	69,00	71,00
Al ₂ O ₃	17,80	17,40	18,50
Fe ₂ O ₃	0,02	0,01	0,03
Na ₂ O	10,40	9,40	11,10
K ₂ O	0,30	0,10	0,40
CaO	0,30	0,20	0,40
LOI	0,30	0,10	0,55

	Tolerance		
	Benchmark	Fra:	Til:
	(%)	(%)	(%)
Finhed:			
>200 µm	< 0,1	0,0	0,5
90 µm	3,2	2,5	3,5
75 µm	6,5	4,5	8,0
60 µm	9,5	8,0	12,0
< 60 µm	90,0	88,0	92,0